

**GRAPHICS - INK-JET DIGITAL**

Issue date : 23/10/2019  
Date last modification : 28/10/2019

**4-GL1G-11012 RI-JET PAPER WALL 230 AP940 WK135**
**Face Material**

Top coated embossed white paper.

Type	Embossed paper		
Colour and Finish	White		
Weight	230 g/m <sup>2</sup> ±10%	ISO-536	
Thickness	400 µ ±10%	ISO 534-80	

**Adhesive**

Acrylic permanent adhesive featuring high clarity and very high cohesion. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	AP940
Type	Acrylic permanent
Min. Appl. Temp.	+10°C
Service Temp.	-30°C/+120°C
Shear	High
Tack	6 N/inch <sup>2</sup>
Final Adhesion	9 N/inch

**Liner**

Type	One side siliconised clay coated Kraft		
Colour and Finish	White		
Weight	135 g/m <sup>2</sup> ±10%	PP-032 - ISO 536	
Thickness	132 µ ±10%	ISO 534	
Transparency	n.a. %	DIN 53 147-64	

**Applications**

Specially designed for interior application on smooth and slightly textured walls, painted household panels and similar substrates.

Flammability: Self-extinguish (ISO 3795)

Durability: UP TO 5 YEARS

The durability data are given for unprinted films only and based on zone 1 vertical exposurei (Northern and Eastern Europe, Italy, France).

**Printing Methods**

Printable with solvent, eco solvent, UV ink-jet and Latex. Testing for suitability between media, printers and inks is always recommended prior to use.

**Shelf life**

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.